

PATENT APPLICATION
ATTORNEY DOCKET NO.: 10/786,974Amendments to the Claims

Please amend the claims 1 through 8 as shown and withdraw claims 9-16.

1. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy ~~comprised~~ consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised of:

approximately ~~29.75% ± 5%~~ 24-34% by weight zinc;

approximately ~~62.15% ± 5%~~ 60-74% by weight copper;

approximately ~~1.35% ± 5%~~ 0.5-1.8% by weight silicon; and

approximately ~~6.75% ± 1.25%~~ 0-8% by weight tin.

2. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~ consisting essentially of:

approximately ~~19.0% ± 5%~~ 19-29% by weight zinc;

approximately ~~74.8% ± 5%~~ 69.8-79.8% by weight copper; and

approximately ~~1.2% ± 5%~~ .7-1.7% by weight silicon.

3. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~ consisting essentially of:

approximately ~~32.60% ± 5%~~ 27.60-37.60% by weight zinc;

approximately ~~64.70% ± 5%~~ 59.7-69.7% by weight copper;

approximately ~~0.60% ± 5%~~ 0.5-1.8% by weight silicon;

approximately ~~0.90% ± 5%~~ 0.90-5% by weight tin; and

approximately ~~1.20% ± 5%~~ 0-1.5% by weight indium.

PATENT APPLICATION
ATTORNEY DOCKET NO.: 10/786,974

4. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant alloy consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 29.75% by weight zinc;
approximately 62.15% by weight copper;
approximately 1.35% by weight silicon; and
approximately 6.75% by weight tin.

5. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 24.0% by weight zinc;
approximately 74.8% by weight copper; and
approximately 1.2% by weight silicon.

6. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

approximately 32.6% by weight zinc;
approximately 64.7% by weight copper;
approximately 0.6% by weight silicon;
approximately 0.9% by weight tin, and
approximately 1.2% by weight indium.

7. (Currently Amended) A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:

92.5 to 95% by weight silver, the balance of which is an alloy comprised consisting essentially of:

PATENT APPLICATION
ATTORNEY DOCKET NO.: 10/786,974

29.75 % by weight zinc;
62.15% by weight copper;
1.35% by weight silicon; and
6.75% by weight tin.

8. A silver-colored, tarnish-resistant, corrosion-resistant jewelry consisting essentially of:
92.5 to 95% by weight silver, the balance of which is an alloy ~~comprised~~
consisting essentially of:

32.60 % by weight zinc;
64.70% by weight copper;
0.60% by weight silicon;
0.90% by weight tin; and
1.20% by weight indium.

9. (Withdrawn).
10. (Withdrawn).
11. (Withdrawn).
12. (Withdrawn).
13. (Withdrawn).
14. (Withdrawn).
15. (Withdrawn).
16. (Withdrawn).

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.